



# PRESERVO

PAINT & COATINGS MANUFACTURING COMPANY

75 Southbelt Industrial Dr. • Houston, TX 77047

Tel: 713.799.9944 • [www.preservo.com](http://www.preservo.com)

## POLYURETHANE ENAMEL P-00 SERIES

### DESCRIPTION:

Polyurethane Enamel is a one can, oil modified, plastic coating that exhibits an extremely tough film which affords good gloss retention and long wear. It has superior flow, good flexibility, excellent mar resistance and is chemical, corrosion and abrasion resistant. Polythane Enamel is readily accepting of an illy prepared surface. This makes it a good choice for use, when it is not possible to properly prepare the surface to a rust-free condition, such as applications out in the field.

### FINISH:

Gloss, Semi-Gloss, Flat

### USES:

Bowling Lanes

Wood

Walls

Maintenance

Farm Equipment

Cabinets-Wood and Metal

Ships and Barges above water line

Shop Equipment

Machinery Equipment

Oil Well Equipment

### FILM PROPERTIES AND BAKE SCHEDULE:

Set To Touch

30 minutes

Re-coat Time

6 To 18 Hours

Complete Cure

7 Days

Times may vary depending on temperature and humidity.

Flash dry for 15 minutes before baking.

150°F For 60 minutes

200°F For 45 minutes

### APPLICATION:

350 Square Feet Per Gallon @ 2 Mils. Apply with Brush, Spray or Roller.

### THINNING AND CLEANUP:

Mineral Spirits or S-10 for faster dry.

### SURFACE PREPARATION:

The surface must be clean and dry. Remove dirt, grease, oil, wax, mildew, loose paint, rust and mill scale.

Glossy, galvanized or metallized surfaces should be treated and primed. Consult a Preservo Paint technician for best results.