



MARINE ENAMEL E-00 SERIES

DESCRIPTION:

Marine Enamel is a one can coating that affords a tough, flexible and impact resistant film. During application, this coating flows easily without lap marks and bubbles. Marine Enamel is formulated with an alkyd resin that conforms to military specification TTR-266D, which produces an excellent coating for wood and a corrosion resistant film for metal surfaces. The surface to be painted must be clean and dry. Remove all dirt, grease, oil, wax, rust, mildew, loose paint and mill scale. Glossy, galvanized or metallic surfaces should be treated and primed. Consult with a Preservo Paint technician in order to achieve the best results.

FINISH:

Gloss, Semi-Gloss, Flat

USES:

Trim Paint	Shop Equipment	Ships and Barges Above Water Line
Wood	Oil Well Equipment	Military Specification

FILM PROPERTIES:

Set To Touch	1 Hour
Re-coat Time	6 to 18 Hours
Complete Cure	7 Days

Times may vary depending on temperature and humidity.

BAKE SCHEDULE:

Flash dry for 15 minutes before baking.
150°F For 60 Minutes
200°F For 45 Minutes
Times may vary depending on temperature and humidity.

APPLICATION:

350 Square Feet per Gallon @ 2 Mils
Apply with brush, spray equipment or with a roller

THINNING AND CLEANUP:

S-09 Mineral Spirits

AVAILABLE IN:

Over 2000 Decorator Colors, Federal Standard 595B, Pearlescents and Metallics.